



# RUST-OLEUM® STOPS RUST® DOOR & TRIM PAINT

## DESCRIPTION AND USES

Rust-Oleum® Door & Trim Advanced Dry Paint dries up to 3X faster than traditional oil based paints and offers ultimate durability with mildew resistance and protection from fading & scuffs. The water-based formula offers low odor, easy application and easy soap & water clean-up. Ideal for metal, wood and fiberglass doors and trim.

## PRODUCTS

SKU	DESCRIPTION (Quart)
369383	Black
369384	White
369385	Cranberry
369386	Nantucket Navy
369387	Alpine Gray
376514	Vermont Green
369389	White/Light Tint Base
369390	Dark Tint Base
369392	Yellow Tint Base
369391	Red Tint Base

## PRODUCT APPLICATION

### SURFACE PREPARATION

For new pre-primed steel, wood doors and fiberglass, simply clean the surface before painting. For best results on bare metal or wood, prime with Zinsser® Bulls Eye 1-2-3® first. For repainting a painted door, remove any loose paint and rust with sandpaper. Lightly sand glossy surfaces. Clean surface with soap and water, rinse and let dry. Paint a small test area in the corner.

**WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

## PRODUCT APPLICATION (cont.)

### PAINTING CONDITIONS

Do not apply to surfaces that will exceed 200°F (93°C). Use when the temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 75% to ensure proper drying. For best results, do not apply in direct sunlight and avoid applying in high temperatures. **PROTECT FROM FREEZING**

### APPLICATION

Before using, stir thoroughly to ensure any settled pigment is re-dispersed. Thinning should not be necessary. If thinning is desired, use up to 5% of water. Recommend application with a 6-1/2" shed resistant roller with a 3/8" nap or a premium quality 2" or 2-1/2" angled sash, 100% nylon or nylon/polyester blend brush. Depending on desired final appearance, a high-density foam roller can also be used. For best results, use the roller to paint the entire door or paint the recessed edges of raised panels and then use the roller for the remaining flat surfaces.

One coat may be enough to fully cover both sides of the door. For new and existing doors, we recommend painting the door off the frame to allow the paint to dry completely before hanging. If painting a hanging door, do not close the door until the paint is fully dry to prevent it from sticking to the door frame. Two coats may be required to develop full color and uniformity.

### DRY & RECOAT TIMES

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures and higher humidity. Dries to touch in 45 minutes, to handle in 4-6 hours, and can be recoated within 1 hour and is fully dry in 6 hours.

### CLEAN-UP

Clean brush and other tools with soap and water.

### COVERAGE

One quart of Rust-Oleum Door & Trim Paint will cover 2 coats on each side of the door.



# RUST-OLEUM® STOPS RUST DOOR & TRIM PAINT

## PHYSICAL PROPERTIES

		DOOR & TRIM PAINT
Resin Type		Acrylic
Pigment Type		Varies with color
Solvents		Water
Weight	Per Gallon	9.5-10.9 lbs.
	Per Liter	1.1-1.3 kg
Solids	By Weight	46.6-54.8%
	By Volume	37.5-40.3%
Volatile Organic Compounds		<50 g/l
Recommended Dry Film Thickness (DFT) Per Coat		2-3 mils (50-75µ)
Wet Film to Achieve DFT		5-8 mils (150-225µ)
Practical Coverage at Recommended DFT		40-65 sq. ft./quart (3.9-6.4 m <sup>2</sup> /l)
Dry Times at 77°F (25°C) and 50% Relative Humidity	Touch	45 minutes
	Handle	4-6 hours
	Recoat	Within 1 hour
	Full Cure	6 hours
Shelf Life		5 years
Flash Point		>200°F
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.