**SharkBite™**

SharkBite™ PEX-a
Blue PEX-a Tubing

SharkBite™ PEX-a is a cross-linked polyethylene tubing designed for use in residential and commercial applications.

Specification Data

Tubing Dimensions

Nominal Size (CTS)	O. D. (in)	Wall Thickness (in)	Approx. I.D. (in)	Weight per ft. (lb.)	Volume per ft. (gal.)
1/2"	0.625 ± 0.004	0.070 + 0.010	0.475	0.053	0.009
3/4"	0.875 ± 0.004	0.097 + 0.010	0.671	0.102	0.018

Tolerances referenced from ASTM F876.

Applications

Potable water distribution, radiant heating, direct burial, embedded in concrete, snow & ice melting, geothermal groundloops, turf conditioning, municipal water service lines, fire suppression & plenum application.

Materials

Cross-Linked Polythethylene / PEX-a / Peroxide Method

Materials Designation Code - PEX 5106

(5) Chlorine Resistance	Rated to continuously recirculate hot water at 140ºF (40ºC)
(1) UV Resistance	One-month UV resistance
(06) Hydrostatic Stress	160 psi @ (33ºF - 70ºF) (0.5ºC - 21ºC) 100 psi @ 180ºF (80ºC) 80 psi @ 200ºF (93ºC)

Certifications & Listings

ASTM F876, ASTM F877, NSF/ANSI 14, NSF/ANSI/CAN 61, NSF/ANSI/CAN 372, ASTM F2023, ASTM F2657, CSA B137.5, UL 1821, ASTM E84CAN/ULC S102.2, ASTM E119CAN/ULC S101

NSF C US C   **QAI**®

Refer to local plumbing code

Part number and description

Part #	PEX Tubing (Coil)
UA60B100	1/2" 100' Coil
UA70B100	3/4" 100' Coil

Part #	PEX Tubing (Straight Length)
UA60B10	1/2" 10' Straight Length
UA70B10	3/4" 10' Straight Length

Bend Radius

Unsupported Bend Radius = 6 X O.D.

Expansion & Contraction Rate

Expansion rate: 1.1" / 10ºF / 100'

For more technical data, visit the product at:
https://www.sharkbite.com/products/potable-pex-a

Product Submittal

Name	
Date	
Architect/Owner	
Contractor	
Tag	
Notes	